

POLITEF (PTFE)25Glass-Fibre
Rods-Sheets

PTFE-GF

			TEST METHOD		VALUES
			ASTM	ISO	
Specific Gravity	g/cm ³		D4894	1183	2,22-2,26
Hardness	Shore D		Needle	-	64-66
Tensile Strength	MPa		D4894	527	Min.18
Elongation	%		D4894	527	25
Diametric Shrinkage	%		Intern	-	2,1

The typical values are average values of the tests done at Polimersan laboratories. Those are for information and not product guarantee values.